

400 - 430W HETEROJUNCTION TECHNOLOGY 223 WM2 POWER DENSITY

> 92% POWER IN YEAR 25


-0.24%/°C TEMPERATURE
COEFFICIENT OF PMAX



# REC ALPHA® PURE-R DATASHEET



**GENERAL DATA** Cell Type 80 half-cut bifacial REC heterojunction cells, with lead-free, gapless technology Glass  $3.2\,\text{mm}\,\text{solar}\,\text{glass}\,\text{with}\,\text{anti-reflective}\,\text{surface}\,\text{treatment}$ in accordance with EN12150 Backsheet Highly resistant polymer (Black) Anodized aluminum (Black) Frame Junction Box 4-part, 4 bypass diodes, lead-free IP68 rated, in accordance with IEC 62790:2020 Stäubli MC4 PV-KBT4/KST4 (4 mm²) Connectors in accordance with IEC 62852:2014, IP68 only when connected Cable  $4 \text{ mm}^2 \text{ solar cable}, 1.40 \text{ m} + 1.40 \text{ m}$ in accordance with EN50618:2014 1730 x 1118 x 30 mm (1.93 m<sup>2</sup>) Dimensions 21.5 kg Weight Origin Made in Singapore



Specifications subject to change without notice.

	Wa
	No
U	No
STC	Op
	Sh
	Po
	Pa

_	
$\frac{8}{2}$	

ELECTRICAL DATA	PRODUCT CODE*: RECXXXAA Pure-R			
Power Output - P <sub>MAX</sub> (WP)	400	410	420	430
Watt Class Sorting - (W)	0/+10	0/+10	0/+10	0/+10
Nominal Power Voltage - $V_{MPP}(V)$	48.8	49.4	50.0	50.5
Nominal Power Current - I <sub>MPP</sub> (A)	8.20	8.30	8.40	8.52
Open Circuit Voltage - $V_{OC}(V)$	58.9	59.2	59.4	59.7
Short Circuit Current - $I_{SC}(A)$	8.80	8.84	8.88	8.91
Power Density (W/m²)	207	212	218	223
Panel Efficiency (%)	20.7	21.2	21.8	22.3
Power Output - P <sub>MAX</sub> (W <sub>p</sub> )	305	312	320	327
Nominal Power Voltage - $V_{MPP}$ (V)	46.0	46.6	47.1	47.6
Nominal Power Current - $I_{MPP}(A)$	6.64	6.70	6.80	6.88
Open Circuit Voltage - V <sub>oc</sub> (V)	55.5	55.8	56.0	56.3
Short Circuit Current - $I_{SC}(A)$	7.11	7.14	7.17	7.20

Values at standard test conditions (STC: air mass AM 1.5, irradiance 1000 W/m², temperature 25°C), based on a production spread with a tolerance of P<sub>MAXV</sub> V<sub>OC</sub> & I<sub>xx</sub> ±3% within one watt class. Nominal module operating temperature (NMOT: air mass AM 1.5, irradiance 800 W/m², temperature 20°C, windspeed 1 m/s). \*Where xxx indicates the nominal power class (P,...) at STC above

#### **TEMPERATURE COEFFICIENT \***

P<sub>MAX</sub> -0.24%/°C

Available from:

V<sub>oc</sub> -0.24%/°C

I<sub>sc</sub> 0.04%/°C

80°C

### **MODULE RATINGS** Module Operating Temperature [T98]§ Min Environmental Temperature

-40°C Nominal Module Operating Temperature 44 ± 2°C Max Hail Rating 35 mm @ 27.2 m/s System Voltage 1000 V Max Series Fuse Rating 25 A 25 A Max Reverse Current

§ 98th percentile operating temperature

#### MAXIMUM TEST LOAD\*

Front (4-Point)\* +7000 Pa (714 Kg/m²) Rear (4-Point)\* -4000 Pa (408 Kg/m²) +8000 Pa (816 Kg/m²) Front (6-Point)\*\* Rear (6-Point)\*\* -6000 Pa (612 Kg/m²) Design load = Test load / 1.5 (safety factor)

\* IEC61730/UL61730 certified. Refer to installation manual. \*\*Internal testing. Refer to installation manual.

#### **CERTIFICATIONS**

ISO 14001; ISO9001; IEC45001; IEC62941		
IEC 61215:2021;IEC 61730:2023;UL 61730		
IEC 61730	Fire Class C (as per UL790)	
ISO 11925-2	Ignitability (EN 13501-1 Class E)	
IEC 62716	Ammonia Resistance (Optional)	
IEC 61701	Salt Mist - SM6 (Optional)	
IEC 61215:2021	Hailstone (35 mm)	
UL 61730	Fire Type 2	
IEC 62321	Lead-free acc. to RoHS EU 863/2015	
IEC TS 63126	Level 1	



WARRANTY







	scheme	
EC P	roTrust	
	Yes	

	Standard	REC ProTrust			
Installed by an REC	No	Yes	Yes		
Certified Professional					
System Size	All	<25 kW	25-500 kW		
Product Warranty (yrs)	20	25	25		
Power Warranty (yrs)	25	25	25		
Labor Warranty (yrs)	0	25	10		
Power in Year 1	98%	98%	98%		
Annual Degradation	0.25%	0.25%	0.25%		
Power in Year 25	92%	92%	92%		
DEC Des Transk Warner translation and Market NDEC and a least fleet before DEC Contribut					


REC ProTrust Warranty applies only for i) REC panels installed by an REC Certified Solar Professional, and ii) panels have been registered by the installer with REC. Subject to System Size and further conditions. See www.recgroup.com for details.

## **DELIVERY INFORMATION**


Panels per Pallet Panels per 40 ft GP/high cube container 858 (26 Pallets) 924 (28 Pallets) Panels per 13.6 m truck

#### LOW LIGHT BEHAVIOUR

Typical low irradiance performance of module at STC:



REC Solar PTE, LTD. 20 Tuas South Ave. 14 Singapore 637312 post@recgroup.com www.recgroup.com



Founded in 1996, REC Group is an international pioneering solar energy company dedicated to empowering consumers with clean, affordable solar power. As Solar's Most Trusted, REC is committed to high quality, innovation, and a low carbon footprint in the solar materials and solar panels it manufactures. Headquartered in Norway with operational headquarters in Singapore, REC also has regional hubs in North America, Europe, and Asia-Pacific

